

DMS Primer 54 *Water Based Primer*

Product description

DMS Primer 54 is a water based primer, for priming of various kinds of metals prior to application of cement flooring onboard ships. Alternatively, between two layers of cement.

Surface preparation

Before the application of DMS Primer 54 there should be a thorough cleaning of the surface, removing all rust, grease, and other contaminations. DMS Primer 54 must be applied with a brush or a roller.

Note: DMS Primer 54 must be used undiluted on steel surface. Between concrete layers DMS Primer 54 can be used in a diluted state 1:1 (1 part DMS Primer 54 and 1 part clean, cold water)

Technical description

Basis	Water based primer
Colour	White
Theoretical covering ability	10 m ² per litre
Flash point	No flash point. Water based
Density	1.0 kg/litre
Pot life	Approx. 15-20 minutes at 20°C and 85 % RH
Drying time at 20° C and 50% RH	Dust dry after approx. 30 minutes. Dry to touch after approx. 1 hour

Note: DMS Primer 54 is not to be used at temperatures below + 5°C

Packaging

- 10 litres cans (60 cans per pallet)

Cleaning

Use water to clean the tools before the primer is cured.

Shelf-life

The shelf-life is min. 12 months in unopened packaging.

Storage

In dry conditions, do not expose to moisture and freezing temperature.

The information and in particular, the recommendations relating to the application and end use of DMS products, are given in good faith based on our current knowledge and experience. The information and recommendations are given without warranty of any kind and does not lead to any further liability for DMS, besides what is stated in the sales agreement. It is the buyer or end-user's responsibility to investigate or in other way make sure that DMS product suitable for the intended use and further are stored, handled and applied in accordance with stated directions. All orders are delivered and accepted in accordance with our general conditions of sale

For additional technical information, please contact our technical department.